

ASIAN EPOXY FINISH PAINT / APCODUR 210



PRODUCT DESCRIPTION

Two component polyamide cured epoxy coating

FEATURES & RECOMMENDED USE

- General purpose finish in epoxy systems for steel exposed to atmospheric land and marine conditions
- Good resistance to water & mild chemicals
- Easy application by brush and spray

TECHNICAL DATA

Colour	Range
Gloss	Semi-glossy
Volume Solids	Approx. 40 %
Recommended DFT / Coat	25 - 35 μ m
Theoretical Coverage Capacity	16.0 sq.mtr/ ltr @ 25 μ m DFT 11.42 sq.mtr/ ltr @ 35 μ m DFT
Drying time at 30°C	Surface Dry : 1 hours Hard Dry : 12 hours Full Cure : 7 days
Over coating interval at 30°C	Min. : 12 hours Max. : 1 month, provided surface is dry and clean from all contamination

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances
The volume solids indicated are as per ASTM D 2697 air drying method
The actual drying time/ overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc.
The information provided above is at 30°C and 65% relative humidity

DIRECTIONS FOR USE

Surface Preparation

General

- Surfaces must be dry, clean and free from contaminants
- Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the coating. Oil and grease should be removed as per SSPC-SP1 solvent cleaning
- Surface should be checked and treated in accordance with ISO 8504 prior to priming
- Suitable epoxy primer or intermediate; dry and free from all surface contamination. In case of aged epoxy coating, the surface should be sufficiently roughened prior to painting

Application Conditions

- Substrate temperature should be at least 3°C above dew point but not above 50°C
- Relative humidity should be below 85%
- Good ventilation is required in confined areas to ensure proper curing

Mixing


- Asian Epoxy Finish Paint / Apcodur 210 is supplied in two packs. Stir the base and hardener separately. If settling is observed in the base or hardener, loosen the settled material with the help of hand stirrer followed by power driven stirrer (at lower RPM) for quick homogenous mixing
- Mix hardener gradually into the base under continuous stirring as per the mixing ratio. Once the unit has been mixed, it should be consumed within the working pot life. In case of part mixing (which should be avoided), close the lids of containers tightly to avoid contact with atmospheric moisture
- Thinner should be added after mixing the components and post the induction time. Addition of excessive thinner will lead to reduced sag resistance

Mixing Ratio (by volume)	Base : Hardener 3 : 1
Induction Time	30 minutes
Pot Life at 30°C	6 hours

Application

Air Spray	
Recommended thinner	T 141
Volume of thinner	0 - 10% *
Nozzle orifice	1.5 – 3.0 mm
Nozzle pressure	0.3 – 0.4 MPa (approx. 3 – 4 atm; 43 – 47 p.s.i.)
Cleaning Thinner	T 141
Airless Spray	
Recommended thinner	T 141
Volume of thinner	0 - 5% *
Nozzle orifice	0.28 - 0.33 mm (11 – 13 Thou)
Nozzle pressure	10 - 13 MPa (approx. 100 - 130 atm; 1400 - 1800 p.s.i.)
Cleaning Thinner	T 141
Brush	
Recommended thinner	T 141
Volume of thinner	0 - 5% *

**Note: Depending on required thickness & application condition*



Cleaning

- Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipment's immediately after use with Thinner T 141. It is recommended to periodically flush out spray equipment during the course of the working day. The frequency of cleaning will depend on amount sprayed, temperature and time gap
- All surplus material and empty containers should be disposed off in accordance with appropriate regional legislations

Product Characteristics

- Maximum film build in one coat is best attained by airless spray. Air spray (pressure pot) may require a multiple cross spray pattern to achieve optimum film build
- The maximum performance is achieved after complete curing
- Minimum two coat application is recommended to provide adequate hiding and uniformity specially when applied by brush
- As common to all epoxy, the product will chalk and discolour on exterior exposure. However these phenomenon are not detrimental to anti-corrosive performance

PACK SIZE	20 L (Base: 15 L & Hardener: 5 L) 4 L (Base: 3 L & Hardener: 1 L) 1 L (Base: 750 ml & Hardener: 250 ml)
STORAGE	Shelf Life: At least 12 months at 30°C for original unopened pack, subject to inspection thereafter. Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash Point: Base: Not less than 24°C; Hardener: Not less than 24°C VOC: Approx. 510 ± 20 gm/ ltr (depending on shades) as per USA-EPA Method 24 Product Weight: Approx. 1.19 ± 0.03 kg/ ltr (depending on shades)

SAFETY INFORMATION

- As a general safety measure, inhalation of solvent vapours or paint mist and contact of liquid paint with skin & eyes should be avoided. Forced ventilation should be provided when applying paint in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying paint
- Please refer our Material Safety Data Sheet prior to using the product

Disclaimer: To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.

'APCODUR' is a Trademark of Asian Paints Ltd. | Licensed user: Asian Paints PPG Pvt. Limited.

Head Office: Asian Paints PPG Private Limited, Plot No-5, Gaiwadi Industrial Estate, S.V. Road, Goregaon (W), Mumbai 400 062
Tel No: 022 62182700, **CIN :** U24110MH2011PTC220557, **Email:** customercare.apppg@asianpaintsppg.com, **Website:** www.asianpaintsppg.com