

PPG SIGMACOVER™ 280

DESCRIPTION

Two-component, aluminum pigmented polyamide cured universal primer

PRINCIPAL CHARACTERISTICS

- General-purpose epoxy primer in protective coating systems for steel and non-ferrous metals
- Excellent adhesion to steel, shop primer, galvanized steel and non-ferrous metals
- Suitable as sealer or tie-coat at DFT 25 - 40 µm (1.0 - 1.6 mils)
- Suitable for immersion service
- Cures at temperatures down to 5°C (41°F)
- Suitable for touching up of weld seams and damages of epoxy coatings during construction
- Suitable on wet blast cleaned substrates (damp or dry)
- Compatible with well-designed cathodic protection systems
- ACQPA 24142-certified

COLOR AND GLOSS LEVEL

- Gray, yellow/green and redbrown
- Low sheen

Note:

- The addition of a UV stable topcoat should be considered when using epoxy coatings in cosmetic areas

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (11.0 lb/US gal)
Volume solids	57 ± 2%
VOC (Supplied)	Directive 2010/75/EU, SED: max. 327.0 g/kg UK PG 6/23(92) Appendix 3: max. 432.0 g/l (approx. 3.6 lb/US gal)
Recommended dry film thickness	50 - 100 µm (2.0 - 4.0 mils) depending on system
Theoretical spreading rate	11.4 m²/l for 50 µm (457 ft²/US gal for 2.0 mils) 5.7 m²/l for 100 µm (229 ft²/US gal for 4.0 mils)
Dry to touch	2 hours
Overcoating Interval	Minimum: 2 hours
Full cure after	7 days
Shelf life	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry

Notes:



PPG SIGMACOVER™ 280

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- Apply this product to the specified thickness as soon as possible after the surface is prepared

Atmospheric exposure conditions

- Steel; blast cleaned to ISO Sa2½ (SSPC SP10), blasting profile 40 – 70 µm (1.6 – 2.8 mils)
- Steel; hand/power tool clean in accordance with St3 or SSPC-SP3 for new building and St2 or SSPC-SP2 for maintenance, UHPWH in accordance with WJ-2L/3L (SSPC-VIS-4)
- Steel with zinc silicate shop primer; pretreated according to ISO Sa1 (SSPC SP7) or hand/power tool cleaned to minimum ISO St2 (SSPC SP2)

Galvanized steel

- The surface must be properly prepared, dry, clean and free of any contamination
- The surface should be sufficiently roughened by sweep blasting to achieve a uniform matt appearance
- Sweep blast in accordance with the SSPC SP16 guidelines

Stainless steel

- The surface must be properly prepared, dry, clean and free of any contamination
- The surface should be sufficiently roughened by sweep blasting with inert non-metallic abrasives
- Sweep blast in accordance with the SSPC SP16 guidelines

Thermal Sprayed Metallization (TSM)

- Surface must be dry and free from any contamination
- The mist coat / full coat technique is required. See mist coat thinning recommendation in the Instructions For Use part below

Concrete / Masonry

- Dried for at least 28 days in good ventilation conditions
- Moisture content should not exceed 4.5%
- Concrete must be sound, dry, free from laitance and any contamination
- Surface should be sufficiently roughened

PPG SIGMACOVER™ 280

Immersion exposure

- Steel; blast cleaned to ISO Sa2½ (SSPC SP10), blasting profile 40 – 70 µm (1.6 – 2.8 mils)
 - Steel with zinc silicate shop primer; weld seams and areas of damaged shop primer or breakdown should be blast cleaned to ISO Sa2½ (SSPC SP10), blasting profile 40 – 70 µm (1.6 – 2.8 mils) or power tool cleaned to ISO St3 (SSPC SP3)
-

Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
 - Relative humidity during application and curing should not exceed 85%
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 4:1

- The temperature of the mixed base and hardener should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
 - Adding too much thinner results in reduced sag resistance and slower cure
 - Thinner should be added after mixing the components
-

Pot life

8 hours at 20°C (68°F)

Note:

- See ADDITIONAL DATA – Pot life
-

Air spray

Recommended thinner

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.5 – 2.0 mm (approx. 0.060 – 0.079 in)

Nozzle pressure

0.3 - 0.4 MPa (approx. 3 - 4 bar; 44 - 58 p.s.i.)

PPG SIGMACOVER™ 280

Airless spray**Recommended thinner**

THINNER 91-92

Volume of thinner

0 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.46 mm (0.018 in)

Nozzle pressure

15.0 MPa (approx. 150 bar; 2176 p.s.i.)

Note:

- Volume of thinner up to 30% for sealer or tie-coat application at DFT range 25 - 40 µm (1.0 - 1.6 mils)

Brush/roller**Recommended thinner**

No extra thinner is necessary

Volume of thinner

Up to 5% THINNER 91-92 can be added if desired

Cleaning solvent

- THINNER 90-53

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
50 µm (2.0 mils)	11.4 m ² /l (457 ft ² /US gal)
75 µm (3.0 mils)	7.6 m ² /l (305 ft ² /US gal)
100 µm (4.0 mils)	5.7 m ² /l (229 ft ² /US gal)

Note:

- Maximum DFT when brushing: 50 µm (2.0 mils)
-

PPG SIGMACOVER™ 280

Overcoating interval for DFT up to 100 µm (4.0 mils)						
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself and various two-pack epoxy coatings	Minimum	12 hours	6 hours	2 hours	1 hour	30 minutes
	Maximum exposed to direct sunshine	3 months	3 months	3 months	2 months	2 months
	Maximum NOT exposed to direct sunshine	6 months	6 months	6 months	4 months	3 months
polyurethane topcoat	Minimum	36 hours	16 hours	6 hours	4 hours	3 hours
	Maximum exposed to direct sunshine	3 months	3 months	3 months	2 months	2 months
	Maximum NOT exposed to direct sunshine	6 months	6 months	6 months	4 months	3 months

Notes:

- Surface should be dry and free from any contamination
- Glossy finishes require a corresponding undercoat

Curing time for DFT up to 100 µm (4.0 mils)			
Substrate temperature	Dry to touch	Dry to handle	Full cure
5°C (41°F)	8 hours	13 hours	21 days
10°C (50°F)	4 hours	6 hours	14 days
20°C (68°F)	2 hours	2.5 hours	7 days
30°C (86°F)	1 hour	1.5 hours	5 days
40°C (104°F)	45 minutes	1 hour	4 days

Note:

- Adequate ventilation must be maintained during application and curing

PPG SIGMACOVER™ 280

Pot life (at application viscosity)	
Mixed product temperature	Pot life
15°C (59°F)	10 hours
20°C (68°F)	8 hours
30°C (86°F)	5 hours
35°C (95°F)	4 hours

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes
- See Safety Data Sheet and product label for complete safety and precaution requirements

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective & Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

- Information sheet | Explanation of product data sheets

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.